

Material data sheet SWG VICTORY ESR

material characteristics	material number / grade	SWG XPM VICTORY ESR						
	short designation	25MnCrNiMoV6-6-4						
	comparable grade	-						
	chemical composition - reference analysis [%]	C	Si	Mn	Cr	Mo	Ni	others
		0.30	0.30	1.55	1.35	0.70	1.00	alloyed
	production technology	EAF/LF/VD, ESR, forging, Q+T						
	service hardness / strength converted acc. to DIN EN ISO 18265 table B2		HB	HRC	N/mm ²			
			359 - 400	38 - 42	1140 - 1270			
	delivery condition	Q+T	359 - 400	38 - 42	1140 - 1270			variation upon request
	maximum dimension	diameter			thickness			
-			≤ 1500 mm					
US-specification	EN 10228-3			SEP 1921				
	table 3 - type 1 - qual. class 4 (t ≤ 800 mm)			group 3 - class E,e (t ≤ 800 mm)				
cleanliness	DIN 50602			ASTM E45 method A				
	K1 ≤ 10			A ≤ 0,5; B, C, D ≤ 1				

technological properties		0	1	2	3	4	5	comment	
	toughness		■	■	■	■			in relation to service hardness
	hot strength at working temp.		■	■	■				
	wear resistance		■	■	■	■			
	corrosion resistance	■							
	machinability		■	■	■			Q+T	
	polishability		■	■	■	■		ISO/SPI: N1/A-1	
	weldability		■	■	■			CET = 0.57 % acc. DIN EN 1011-2	
	texturability		■	■	■	■	■		
	nitridability		■	■	■			nitriding hardness 550 - 700 HV1	
chrome-platability		■	■	■	■	■			

rating properties: 0 = not suitable; 1 = low; 2 = middle; 3 = good; 4 = very good; 5 = perfectly suitable

physical properties	thermal conductivity [W · m ⁻¹ · K ⁻¹]	20 °C	200 °C	300 °C	500 °C
		37.1	39.0	38.5	37.1
	coefficient of thermal expansion between 20 °C and ... [10 ⁻⁶ · K ⁻¹]	100 °C	200 °C	300 °C	500 °C
		12.2	12.5	13.1	14.8
elastic modulus [kN/mm ²]	20 °C	200 °C	300 °C	500 °C	
	212	207	192	175	

Material data sheet SWG VICTORY ESR

application	technology	mold making, injection molding, press-molding
	tools	plastic molds and cavities, with highest surface requirements
	process temperature	< 250 °C
	tool size	small-, medium- and large-sized molds
	final products	transparent plastic parts, high gloss parts, car lights
	features	high homogeneity and cleanliness


SWG processing instructions	welding, texturing, polishing, deep-hole drilling
-----------------------------	--

heat treatment		T min [°C]	T max [°C]	medium / comment
	annealing	710	740	air
	hardening	870	920	oil, polymer
	tempering	540	650	air
	stress relieving	500	530	min. 30 °C below tempering temp.
	pre-heating before welding	300	330	
	nitriding	450	530	min. 30 °C below tempering temp.
	PVD-treating	450	530	


diagrams/ structure	CCT-diagram	yes
	tempering diagram	yes
	advice on heat treatment	pre-hardened
	microstructure	mainly bainitic

Material data sheet SWG VICTORY ESR

Tempering diagram: Average values on samples dia 25 mm x length 50 mm; hardened at 880 °C in oil



CCT-diagram



PLEASE NOTE: The information contained in this data sheet is unbinding. It merely serves the first orientation of the user. Therefore, we do not assume any liability for the correctness, completeness or up-to-dateness of such data. In case of an order, the properties of the product are exclusively subject to the provisions of the respective contract.
© Schmiedewerke Gröditz GmbH, Gröditz